

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWAP 1261

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)- Dry	Min: 0.51	ASTM
Moisture (% by wt) - As packed	Max: 5	ASTM
Total Ash (% by wt)	Max: 3	ASTM
Hardness No.	Min: 98	ASTM
Extractable pH	8-11	ASTM
Particle size 12X40 ASTM mesh		
> 12 mesh (1.70 mm) (% by wt)	Max. 5	ASTM
12 X 40 mesh (1.70 mm x 0.425 mm) (% by wt)	Min. 90	ASTM
< 40 mesh (0.425 mm) (% by wt)	Max. 5	ASTM

Spec No: 6752



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTFU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified



www.haycarb.com