

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWAP 1442

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g)	Min: 1000	ASTM D4607
Apparent Density (g/cc)- Dry	Min: 0.50	ASTM D2854
Moisture (% by wt) - As packed	Max: 5	ASTM D2867
Total Ash (% by wt)	Max: 3	ASTM D2866
Hardness No.	Min: 98	ASTM D3802
Extractable pH	8-11	ASTM D3838
<u>Particle size 6X12 ASTM mesh</u>		ASTM D2862
> 6 mesh (3.350 mm) (% by wt)	Max. 5	
6 X 12 mesh (3.350 mm x 1.700 mm) (% by wt)	Min. 90	
< 12 mesh (1.700 mm) (% by wt)	Max. 5	

* NSF CERTIFIED , WATER WASHED PRODUCT.

Spec No: 8530

Date : 16-Dec-2020



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTFU

Component



ISO 9001:2008 Certified



ISO 14001:2004 Certified

www.haycarb.com