

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWAP 6069

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g) - Base	Min: 1000	ASTM
Apparent Density (g/cc)- Dry- Base	Min: 0.51	ASTM
Moisture (% by wt) - As packed	Max: 8	ASTM
Total Ash (% by wt)	Max: 3	ASTM
Hardness No.	Min: 98	ASTM
Silver Loading Content (% by wt)	Min: 0.15	HC STP
Silver Leaching (ppb)	Max: 50	HC STP
Nitrate Leaching (ppm)	Max: 50	HC STP
Nitrite Leaching (ppm)	Max: 0.1	HC STP
Particle size 8X30 ASTM mesh		
> 8 mesh (2.36 mm) (% by wt)	Max. 5	ASTM
8X30 mesh (2.36 mm x 0.60 mm) (% by wt)	Min. 90	ASTM
< 30 mesh (0.60 mm) (% by wt)	Max. 5	ASTM

Spec No: 6753



Haycarb Activated Carbon grades that are Tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on: www.nsf.org/certified/DWTU

Component



ISO 14001:2004 Certified

www.haycarb.com