

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWNO 1001

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)- Dry	Min: 0.51	ASTM
Moisture (% by wt) - As packed	Max: 5	ASTM
Total Ash (% by wt)	Max: 3	ASTM
Hardness No.	Min: 98	ASTM
Extractable pH	9-11	ASTM
<u>Particle size 8X30 ASTM mesh</u>		
> 8 mesh (2.36 mm) (% by wt)	Max. 5	ASTM
8X30 mesh (2.36 mm x 0.60 mm) (% by wt)	Min. 90	ASTM
< 30 mesh (0.60 mm) (% by wt)	Max. 5	ASTM

Spec No: 6749