

PRODUCT SPECIFICATION

REFERENCE NO: QAP / 03 / D4



HAYCARB
Activated carbon solutions

RWNO 1002

SPECIFICATION	VALUE	TEST METHOD
Iodine Number (mg/g)	Min: 1000	ASTM
Apparent Density (g/cc)- Dry	Min: 0.51	ASTM
Moisture (% by wt) - As packed	Max: 5	ASTM
Total Ash (% by wt)	Max: 3	ASTM
Hardness No.	Min: 98	ASTM
Extractable pH	9-11	ASTM
<u>Particle size 12X40 ASTM mesh</u>		
> 12 mesh (1.70 mm) (% by wt)	Max. 5	ASTM
12 X 40 mesh (1.70 mm x 0.425 mm) (% by wt)	Min. 90	ASTM
< 40 mesh (0.425 mm) (% by wt)	Max. 5	ASTM

Spec No: 6750